

Neutrals Range Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Swatch Image	State	Length	Width	Height	Dimensional Category	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
Neutrals Range	Dove		NSW	230	110	76	DW1	48.5	520	>15	Slight	Slight	0.43	41.3	Light	90/90/90
Neutrals Range	Natural Linen		NSW	230	110	76	DW1	48.5	520	>15	Slight	Slight	0.44	37.3	Light	90/90/90
Neutrals Range	Canvas		NSW	230	110	76	DW1	48.5	520	>15	Slight	Slight	0.64	19.2	Medium	90/90/90
Neutrals Range	Oatmeal		NSW	230	110	76	DW1	48.5	520	>15	Slight	Slight	0.51	31.1	Medium	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.