

Traditional Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix
Traditional	Chapel Red			NSW	230	110	76	DW1	4.2	48.5	400	>10	>10	0.5-2.5	Exposure Grade	Slight	Slight	0.73	9.4	Dark
Traditional	Lygon Coffee			NSW	230	110	76	DW1	4	48.5	400	>10	>10	0.5-2.5	Exposure Grade	Slight	Slight	0.71	11.6	
Traditional	Acland Cream			NSW	230	110	76	DW1	4.1	48.5	400	>10	>10	0.5-2.5	Exposure Grade	Slight	Slight	0.51	27.3	Medium

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.